


Thread bar



Designation Symbol	Yield Strength N/mm ²	Tensile strength N/mm ²	Elongation %	Relaxation Value %	Unit mass kg/m	Nominal diameter		Measurement of thread area			
						dh mm	dv mm	Height a mm	Width b mm	Pitch c mm	Lead angle α °
23 mm	930 min.	1080 min.	6.0 min.	4.0 max.	3.42	23.0	23.0	1.40	5.5	12.0	81.0
	930 min.	1180 min.									
26 mm	930 min.	1080 min.									
	930 min.	1180 min.									
32 mm	930 min.	1080 min.									
	930 min.	1180 min.									
36 mm	930 min.	1080 min.									

Sales Department
Special Steel Wire Division
ADDRESS: 1-1-1, Koya-Kita, Itami, Hyogo 664-0016 Japan
TEL: +81-72-771-0966
FAX: +81-72-771-0502
E-MAIL: pc-int@info.sei.co.jp
URL: <http://www.sei-ssw.co.jp/>

